March 1, 2006

DURAFOAM™ C121A SERIES

TYPICAL PHYSICAL PROPERTIES

Stock No.	DURAFOAM™ C121A	DURAFOAM™ C221A
Color	Black	Black
Polymer	Neoprene/SBR	Neoprene/SBR
Density, pcf, approx.	4.5	5
SAE J18 July 92	2A1	2A2
ASTM-D-1056-67	SCE 41	SCE 42
ASTM D1056-68 & 78	RE 41	RE 42
ASTM D1056-85, 91, 98 & 00	2A1	2A2
Compression Deflection, 25% psi Compression, Varies with Thickness	2 to 5 psi	5 to 9 psi
Water Absorption by Weight (Max) ASTM Method D 1056	5% (10% allowed)	5% (10% allowed)
Flame Resistance, FMVSS302	Pass	Pass

"0" EMISSIONS – GUARANTEED TO BE 100% RECYCLABLE

AVAILABLE IN:

BUNS

SHEETS

ROLLS

TAPE

AUTOMOTIVE GASKETING SOLUTIONS

PHYSICAL AND SHOCK ATTENUATION TEST LABORATORY

75 LONG BRANCH AVENUE, LONG BRANCH, NJ 07740

PHONE 888-FOAM-888 EXT. 13 FAX 800-375-1962

E-mail sales@monmouthrubber.com Internet http://www.rubberplastics.com